

CENUSIL[®] M 830 A/B

Room Temperature Curing Silicone Rubber (RTV-2)

is a pourable, addition-curing RTV-2 silicone rubber that cures at room temperature.

Main application: Making molds for concrete casting.

Food contact (FDA/ BfR compliant).



Properties

- good flow ability and self-deaeration
- proper tear strength
- universal hardness (26 Shore A)
- easy to meter and mix due to 1 : 1 ratio
- perfect and non-shrink cure at room temperature which can be accelerated considerably by the application of heat
- excellent long- term stability of the mechanical properties of the vulcanizate
- good resistance to common reproduction materials

Special features

- BfR compliant
- FDA compliant

Technical data

Properties Uncured

| Property | Condition | A | B | Method |
|--------------------|-----------|------------------------|------------------------|----------|
| Viscosity, dynamic | 23 °C | 8000 mPa·s | 8000 mPa·s | ISO 3219 |
| Density | 23 °C | 1.05 g/cm ³ | 1.05 g/cm ³ | ISO 2811 |
| Color | - | translucent | translucent | - |

These figures are only intended as a guide and should not be used in preparing specifications.

Properties Catalyzed A+B

| Property | Condition | Value | Method |
|-------------------------|-----------|-------------|--------|
| Pot life ⁽¹⁾ | - | 60 min | - |
| Mix ratio | - | 1 : 1 | - |
| Color | - | translucent | - |
| Demoldable after | - | 14 - 16 h | - |

¹(up to 100000 mPa·s)

These figures are only intended as a guide and should not be used in preparing specifications.

Properties Cured

After 24 hours at 23 °C

| Property | Condition | Value | Method |
|---------------------|-----------|---------------------|--------------|
| Elongation at break | - | 500 % | ISO 37 |
| Tensile strength | - | 5 N/mm ² | ISO 37 |
| Hardness Shore A | - | 26 | ISO 868 |
| Tear strength | - | > 20 N/mm | ASTM D 624 B |

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

Applications

- Construction Molding
- Reproduction molding for foundry, arts and handicraft

Application details

As a medium-Shore A addition RTV-2 silicone rubber that cures without undergoing dimensional shrinkage, CENUSIL® M 830 A/B is extremely suitable for casting all common reproduction materials.

Processing

Important note:

The platinum catalyst is contained in **Component A**

Caution

A and B components may only be used together if they have the same batch number.

To ensure optimum flow of the material, the components must be stirred thoroughly before they are removed, or processed in their containers.

Please check also our brochures and info sheets.

Packaging and storage

Packaging

- CENUSIL® M 830 A 20 KG HOBBOCK PE
- CENUSIL® M 830 A 200 KG DRUM SB
- CENUSIL® M 830 B 20 KG HOBBOCK PE
- CENUSIL® M 830 B 200 KG DRUM SB

Storage

The 'Best use before end' date of each batch is shown on the product label.

Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Safety notes

Components A and B of the addition-curing grade CENUSIL® M 830 A/B contain only constituents that over many years have proved to be neither toxic nor aggressive. Special handling precautions are therefore not required, i.e., only the general industrial hygiene regulations apply.

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from WACKER subsidiaries or may be printed via WACKER web site <http://www.wacker.com>.

QR Code CENUSIL® M 830 A/B



For technical, quality or product safety questions, please contact:

Wacker Chemie AG, Hanns-Seidel-Platz 4, 81737 Munich, Germany
info@wacker.com, www.wacker.com

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.